

Test Report - CSP

Dry :72 °F Wet :64 °F RH : 63.00 % Test Date & Time : 20-May-25 11:37 am
Test ID :44518 No. of Test :10 Count Type :20/1 CCH Nom. Strength :145 (lbf)
Dept. :Finishing Lot No. : Nom. Count :20.0 (NeC) Sam. Length :120.00 yard
Shift :General Operator :Owner

Machine : Fin 16	Test No.	Weight (g)	Count (NeC)	RH Count (NeC)	Strength (lbf)	CSP	RH CSP
	1	3.187	20.329	20.304	145.02	2948	2945
	2	3.170	20.441	20.417	136.65	2793	2790
	3	3.221	20.114	20.090	149.32	3003	3000
	4	3.176	20.401	20.376	138.21	2820	2817
	5	3.140	20.633	20.608	134.87	2783	2780
	6	3.278	19.764	19.740	152.02	3005	3002
	7	3.203	20.229	20.205	146.84	2970	2967
	8	3.182	20.361	20.336	144.02	2932	2929
	9	3.245	19.966	19.941	150.65	3008	3005
	10	3.191	20.305	20.280	141.02	2863	2861
	Average	3.199	20.254	20.230	143.86	2913	2910
	CV %		1.23	1.23	4.18	3.09	3.09
	Min.		19.764	19.740	134.87	2783	2780
	Max.		20.633	20.608	152.02	3008	3005
	Range		0.869	0.868	17.15	225	225
	SD		0.25	0.25	6.01	89.98	89.92
	Q95 (±)		0.18	0.18	4.24	63.40	63.35
	Q99 (±)		0.25	0.25	90.17	90.17	90.11

RKM Value : 18.642 RH RKM Value : 18.624

Remarks : 20/1 CCH.....CONDITION

CHECKED BY

QAD

PM

MM

GM

